



Title: Sound Absorption Test Results

Product: 2 Layers of 1" Echo Eliminator

Application: Wall and Ceiling

Testing Standard: ASTM C423 A-Mount


Test Date: 09/26/2000

Why this test: This test evaluates a products efficiency of absorbing sound at multiple frequencies. The test simulates the product's acoustical performance with a direct installation on a wall or ceiling.

Test Result Summary: NRC - 1.05; SAA - 0.90

NRC	SAA
1.05	0.90

Frequency (Hz)	Absorption Coefficient
100	0.18
125	0.17
160	0.24
200	0.45
250	0.63
315	0.89
400	1.09
500	1.15
630	1.22
800	1.21
1000	1.21
1250	1.22
1600	1.18
2000	1.15
2500	1.16
3150	1.15
4000	1.08
5000	0.84



Test ID: 18 0-0730.5

ASI TEST RESULT DISCLAIMER

ASI makes every effort to ensure the accuracy and reliability of the information provided. Laboratory testing is conducted by independent testing organizations. ASI does not guarantee that field tests or independent tests will not vary.

PROJECT NUMBER: 18 0-0730.5

PAGE: 1 of 3

DATE: September 26, 2000

STOCK / TWIN CITY TESTING CORPORATION
662 Cromwell Avenue
St. Paul, Minnesota 55114

SOUND ABSORPTION TESTING CONDUCTED
ON A WALL PANEL CONSISTING OF TWO LAYERS
OF BAFP NOISE STOP ECHO ELIMINATOR™
ACOUSTICAL RECYCLED COTTON INSULATION

Prepared for:
ACOUSTICAL SURFACES – DIVISION OF
ARCHITECTURAL SURFACES, INC.
Attn: Mr. Steve Anderson
123 Columbus Court North, Suite 201
Chaska, MN 55318

Client Purchase Order Number 00012348

Test Conducted By:



Matthew N. Botz
Project Engineer
Product Testing Department
(651) 659-7353

Reviewed By:



Richard O. Thomalla
Acoustical Services Manager
Product Testing Department
(651) 659-7310

The test results contained in this report pertain only to the samples submitted for testing and not necessarily to all similar products.

An Affirmative Action



Equal Opportunity Employer



PROJECT NUMBER: 18 0-0730.5

PAGE: 2 of 3

DATE: September 26, 2000

SOUND ABSORPTION - ASTM C423-99a

INTRODUCTION:

This report presents the results of Sound Absorption testing conducted on a wail panel consisting of two 1" layers of Noise Stop Echo Eliminator™ BAFP insulation submitted by Acoustical Surfaces. This work was requested by Mr. Mike Nixon on September 6, 2000 with the testing conducted on September 14, 2000.

This report must not be reproduced except in its entirety with the approval of Stork / Twin City Testing Corporation. The data in this report relates only to the item tested.

Stork / Twin City Testing Corporation has been accredited by the U.S. Department of Commerce and the National Institute of Standards and Technology (NIST, formerly NBS) under their National Voluntary Laboratory Accreditation Program (NVLAP) for conducting this test procedure. This report may not be used to claim product endorsement by NVLAP or any agency of the U.S. Government.

TEST RESULTS SUMMARY:

The Noise Reduction Coefficient (NRC) value of the tested specimen was **1.05**. A detailed data sheet is provided below under "TEST RESULTS".

TEST PROCEDURE:

ASTM: C423-99a, "Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method" was followed in every respect. Sixteen- 2' x 4' x 1" panels were joined together to make one extended plane surface of 64 square feet (8' x 8' x 2") which was then placed on the floor of the reverberation chamber. Further mounting and configuration details are provided under "TEST RESULTS" below.

Absorption coefficients are the fraction of diffuse incident sound absorbed by the specimen and are expressed in sabins per square foot. The NRC is the average of the absorption coefficients for 250, 500, 1000, and 2000 Hertz and is reported to the nearest integral of 0.05.

TEST EQUIPMENT:

<u>Manufacturer</u>	<u>Model</u>	<u>Serial #</u>	<u>Description</u>
Norwegian Electronics	NE830	11511	Real Time Spectrum Analyzer
Brüel & Kjær	3923	815424	Rotating Microphone Boom
Larson-Davis	2560	1032	Pressure Condenser Microphone
Compaq Computer	V20 CIO	A942CZGZE580	Custom Designed Software

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document

PROJECT NUMBER: 18 0-0730.6

PAGE: 3 of 3

DATE: September 26, 2000

TEST RESULTS:

Manufacturer : Acoustical Surfaces
Type : Wall Panel – 2 - 1" layers of BAFF.
Dimensions (W x H x D) : 2.0' x 4.0' x 21"
Weight : 37 lbs. (0.58 psf)
Surface Area : 8.0 ft²
Total Surface Area : 64.0 ft² – consisting of 6 panels - (2 layers)
Mounting Type : Type A

Test No. 18 0-0730.5

Frequency Hz	Absorption Coefficients	Absorption (Sabins)
100	0.18	11.82
125	0.17	10.93
160	0.24	15.50
200	0.45	29.08
250	0.63	40.59
315	0.89	57.11
400	1.09	69.49
500	1.15	73.86
630	1.22	78.30
800	1.21	77.47
1000	1.21	77.95
1250	1.22	77.83
1600	1.18	75.28
2000	1.15	73.72
2500	1.16	74.56
3150	1.15	73.38
4000	1.08	69.27
5000	0.84	53.67

Noise Reduction Coefficient (NRC) = 1.05

The NRC frequencies are at 250, 500, 1000, and 2000 Hz

G:\MMFILES\SKM\0730-5.ABS

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document