



Title: Sound Absorption Test Results

Product: 3 baffles - 1" Echo Eliminator

Application: Ceiling


Testing Standard: ASTM C423 with baffles suspended on two cables - 36" spacing between baffles - 45" spacing between cables

Test Date: 09/26/2000

Why this test: This test evaluates a products efficiency of absorbing sound at multiple frequencies. The test simulates the product's acoustical performance installed as hanging baffles.

Test Result Summary: Sabins / Baffle average at NRC frequencies - 9.55

Sabins / Baffle average at NRC frequencies	
9.55	
Frequency (Hz)	Absorption (Sabins/Baffle)
100	3.05
125	2.72
160	2.07
200	4.01
250	4.61
315	5.37
400	6.79
500	7.71
630	8.71
800	10.02
1000	11.62
1250	13.24
1600	13.78
2000	14.29
2500	14.77
3150	14.98
4000	15.77
5000	14.72



Test ID: 18 0-0730.14

ASI TEST RESULT DISCLAIMER

ASI makes every effort to ensure the accuracy and reliability of the information provided. Laboratory testing is conducted by independent testing organizations. ASI does not guarantee that field tests or independent tests will not vary.

PROJECT NUMBER: 18 0-0730.14

PAGE: 1 of 3

DATE: September 26, 2000

STOCK / TWIN CITY TESTING CORPORATION
662 Cromwell Avenue
St. Paul, Minnesota 55114

SOUND ABSORPTION TESTING CONDUCTED
ON THREE BAFFLES CONSISTING OF
1" THICK BAFP INSULATION

Prepared for:
ACOUSTICAL SURFACES – DIVISION OF
ARCHITECTURAL SURFACES, INC.
Attn: Mr. Steve Anderson
123 Columbus Court North, Suite 201
Chaska, MN 55318


Client Purchase Order Number 00012348

Test Conducted By:



Matthew N. Botz
Project Engineer
Product Testing Department
(651) 659-7353

Reviewed By:



Richard O. Thomalla
Acoustical Services Manager
Product Testing Department
(651) 659-7310

The test results contained in this report pertain only to the samples submitted for testing and not necessarily to all similar products.

An Affirmative Action



Equal Opportunity Employer



PROJECT NUMBER: 18 0-0730.14

PAGE: 2 of 3

DATE: September 26, 2000

SOUND ABSORPTION - ASTM C423-99a

INTRODUCTION:

This report presents the results of Sound Absorption testing conducted on three baffles consisting of 1" thick BAFP insulation submitted by Acoustical Surfaces. This work was requested by Mr. Mike Nixon on September 6, 2000 with the testing conducted on September 13, 2000.

This report must not be reproduced except in its entirety with the approval of Stork / Twin City Testing Corporation. The data in this report relates only to the item tested.

Stork / Twin City Testing Corporation has been accredited by the U.S. Department of Commerce and the National Institute of Standards and Technology (NIST, formerly NBS) under their National Voluntary Laboratory Accreditation Program (NVLAP) for conducting this test procedure. This report may not be used to claim product endorsement by NVLAP or any agency of the U.S. Government.

TEST RESULTS SUMMARY:

The Sabins / Baffle average of the tested specimens was **9.55** at the NRC frequencies of 250, 500, 1000 and 2000 Hertz. A detailed data sheet is provided below under "TEST RESULTS".

TEST PROCEDURE:

ASTM: C423-99a, "Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method" was followed in every respect. The baffles were suspended above the floor of the reverberation chamber on cables. The full mounting and and configuration details are provided under "TEST RESULTS" below.

TEST EQUIPMENT:

<u>Manufacturer</u>	<u>Model</u>	<u>Serial #</u>	<u>Description</u>
Norwegian Electronics	NE830	11511	Real Time Spectrum Analyzer
Brüel & Kjær	3923	815424	Rotating Microphone Boom
Larson-Davis	2560	1032	Pressure Condenser Microphone
Compaq Computer	V20 CIO	A942CZGZE580	Custom Designed Software

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document

PROJECT NUMBER: 18 0-0730.14

PAGE: 3 of 3

TEST RESULTS:

DATE: September 26, 2000

Manufacturer : Acoustical Surfaces
Type : Baffles – 1" layer BAFP.
Dimensions (W x H x D) : 2' x 4' x 1"
Weight : 7 lbs. (0.29 psf)
Surface Area : 8.0 ft²
Total Surface Area : 48.0 ft² – consisting of 3 baffles-(2 sides)
Mounting Type : 3 specimens suspended between 2 cables-36" between baffles -
(Note: Baffles suspended at an angle between cables to maintain uniform height)

Test No. 18 0-0730.14

Frequency Hz	Absorption Coefficients)
100	3.05
125	2.72
160	2.07
200	4.01
250	4.61
315	5.37
400	6.79
500	7.71
630	8.71
800	10.02
1000	11.62
1250	13.24
1600	13.78
2000	14.29
2500	14.77
3150	14.98
4000	15.77
5000	14.72

Sabins / Baffle Average (NRC Frequencies) = 9.55
The NRC frequencies are at 250, 500, 1000, and 2000 Hz

Information and statements in this report are derived from material, information and/or specifications furnished by the client and exclude any expressed or implied warranties as to the fitness of the material tested or analyzed for any particular purpose or use. This report is the confidential property of our client and may not be used for advertising purposes. This report shall not be reproduced except in full, without written approval of this laboratory. The recording of false, fictitious or fraudulent statements or entries on this document